

5

ABSTRACT OF THE DISCLOSURE

10 A copper-clad laminate is composed of a polyimide
film and an electrolytically plated copper film placed on
at least one surface side of the polyimide film, in which
the copper film has at most 200 protrusions having a
diameter of 15 μm or more on its surface not facing the
polyimide film, and the laminate has a peel strength of 1
kgf/cm or more and shows a peel strength of 0.6 kgf/cm or
15 more after heating at 150°C for 24 hours.